

PAT-NO:

JP406275982A

DOCUMENT-IDENTIFIER: JP 06275982 A

TITLE: RADIO WAVE ABSORBING BODY

PUBL-DATE: September 30, 1994

INVENTOR-INFORMATION:

NAME

WATANABE, KEIICHI

MORI, KOJI

KOSHIISHI, KENJI

1, 2, 5, 6

ASSIGNEE-INFORMATION:

NAME

NISSHIN STEEL CO LTD

COUNTRY

N/A

APPL-NO: JP05088121

APPL-DATE: March 23, 1993

INT-CL (IPC): H05K009/00

US-CL-CURRENT: 174/32

ABSTRACT:

PURPOSE: To provide a cheap radio wave absorbing body which is higher in radio wave absorbing properties than a conventional one without using specific ferrite and employing a multilayered structure by a method wherein a specific amount of metal oxide is fixed into binder which is compounded with ferrite.

CONSTITUTION: Ferrite compounded with binder is molded into a radio wave absorbing body by heating, wherein 25mass% of metal oxide or below is mixed

BEST AVAILABLE COPY

into binder. It is preferable that the mixing amount of binder ranges from 5 to 20mass%, and it is also preferable that titanium oxide is used as metal oxide. For instance, Mn-Zn ferrite is mixed into methyl methacrylate or styrene solution and heated at a temperature of 50&deg;C for 24 hours for polymerization in the presence of AIBN catalyst, whereby the surface of ferrite is uniformly coated with methyl polymethacrylate (PMMA) or polystyrene (PSt). Then, resin-coated ferrite is put into a molding die, heated at a temperature of 170&deg;C or 250&deg;C for 10 minutes, and molded into a radio wave absorbing body.

COPYRIGHT: (C)1994,JPO&Japio

BEST AVAILABLE COPY